

Hempel's AntiFouling Globic 7000

Product characteristics

Description

Hempel's Antifouling Globic 7000 is a high solids chemically hydrolysing SPC antifouling based on Nano Acrylate Technology (NAT). Globic 7000 offers low friction, self-smoothening, and a best-inclass instant activation of polishing for optimal performance from day one. The NAT is therefore especially good for slower steaming and frequent idle days due to the strong biocide package with 3 biocides, very thin leach-layer and fine control of polishing. The patented microfibers give Globic 7000 a best-in-class mechanical strength to avoid cracking and peeling.

This product does not contain organotin compounds acting as biocides and complies with the International Convention on the Control of Harmful Antifouling Systems on Ships as adopted by IMO October 2001 (IMO document AFS/CONF/26).

Recommended use

For both newbuildings and maintenance of underwater hull and boottop for up to 60 months drydocking interval.

Product safety

Flash point 24°C [75°F]

VOC content

| Legislation | Value | |
|-----------------|--------------------------|--|
| EU | 381 g/L [3.18 lb/US gal] | |
| US (coatings) | 381 g/L [3.18 lb/US gal] | |
| US (regulatory) | 381 g/L [3.18 lb/US gal] | |
| China | 381 g/L [3.18 lb/US gal] | |

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

78350

Standard shade / code Brownish red 51110 *

Gloss Flat

Volume solids

58 ± 2%

Specific gravity

1.7 kg/L [14 lb/US gal]

Reference dry film thickness

100 micron [3.9 mils]

Surface preparation

New build:

- According to Hempel's Specification.

Maintenance and Repair

- Remove salts, detergents, contaminants and marine growth by high pressure fresh water cleaning.
- Sealer: Whether to use a sealer coat/tiecoat or not depends on the type and condition of the existing antifouling.

Consult Hempel's separate Surface Preparation Guidelines for more details.

Application

Mixing ratio

This product contains heavy particles. Stir well before use. In general, thinning is not recommended.

Thinner

Hempel's Thinner 08080



Hempel's AntiFouling Globic 7000

Cleaner

Hempel's Thinner 08080

Application method

| Tool | Thinning max vol. | Application parameters |
|---------------|-------------------|---|
| Airless spray | 5% | Nozzle pressure: 270 bar [3900 psi] Nozzle orifice: 0.027-0.031" |

Filter: surge tank filter and tip filter should be removed. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

| Specification range | Low | High | Recommended | |
|---|------------|-----------------------------------|-----------------------------------|--|
| Dry film thickness | 80 micron | 150 micron | 100 micron | |
| | [3.1 mils] | [5.9 mils] | [3.9 mils] | |
| Wet film thickness | 130 micron | 270 micron | 175 micron | |
| | [5 mils] | [10 mils] | [7 mils] | |
| Theoretical spreading rate 7.2 m²/L [290 sq ft/US gal] | | 3.8 m²/L [150 sq ft/US gal] | 5.8 m²/L [240 sq ft/US gal] | |

Application conditions

 To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Application remarks

- Copper containing antifouling must not have any electrical contact with aluminium hull and other aluminium components.

Drying and overcoating

Product compatibility

- Previous coat: According to Hempel's Specification. Recommended products are: Hempadur Tiecoat 49183, Hempadur 47182.
- Subsequent coat: None or according to Hempel's specification.

Drying time

| Surface temperature | | 10°C [50°F] | 20°C [68°F] |
|---------------------|-----|-----------------------|-----------------------|
| Hard dry | min | 120 | 60 |

Determined for dry film thickness 100 micron [3.9 mils] at standard conditions, see Hempel's Explanatory Notes for details.

Drying conditions

 To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

Overcoating details

- The surface must be dry and clean prior to application.
- Consult Hempel for specific details

Other remarks

- Consult Hempel for information on the minimum undocking time.

Storage

Shelf life

| Ambient | 25°C |
|-------------|-----------|
| temperature | [77°F] |
| Product | 36 months |

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.



Hempel's AntiFouling Globic 7000

Additional documents

Additional information is available at the Hempel website https://www.hempel.com/service-and-support/technical-guidelines or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

| No. | Document description | Location/comments |
|-----|--|---|
| 1. | Technical Statement | One-off specific advice provided on request for specific projects |
| 2. | Specification | Only issued for specific projects |
| 3. | PDS | This document |
| 4. | Explanatory Notes to the PDS | Available at www.hempel.com and contain relevant information about the Product testing parameters |
| 5. | Application Instruction | Where available, at www.hempel.com |
| 6. | Generic technical guidelines (e.g. on application and surface preparation) | Where available, at www.hempel.com |

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.

hempel.com Issued by Hempel A/S - March 2023